

Accepted Article Preview: Published ahead of advance online publication



## Microcavity electrodynamics of hybrid surface plasmon polariton modes in high-quality multilayer trench gratings

Xiaoyi Liu, Jinbo Gao, Jinsong Gao, Haigui Yang, Xiaoyi Wang, Tongtong Wang, Zhenfeng Shen, Zhen Liu, Hai Liu, Jian Zhang, Zizheng Li, Yanchao Wan and Qiang Li

Cite this article as: Xiaoyi Liu, Jinbo Gao, Jinsong Gao, Haigui Yang, Xiaoyi Wang, Tongtong Wang, Zhenfeng Shen, Zhen Liu, Hai Liu, Jian Zhang, Zizheng Li, Yanchao Wan and Qiang Li. Microcavity electrodynamics of hybrid surface plasmon polariton modes in high-quality multilayer trench gratings. *Light: Science & Applications* accepted article preview 1 March 2018; doi: 10.1038/s41377-018-0009-x

This is a PDF file of an unedited peer-reviewed manuscript that has been accepted for publication. NPG are providing this early version of the manuscript as a service to our customers. The manuscript will undergo copyediting, typesetting and a proof review before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers apply.

Received 1 November 2017; revised 8 February 2018; accepted 24 February 2018;  
Accepted article preview online 1 March 2018

# Microcavity electrodynamics of hybrid surface plasmon polariton modes in high-quality multilayer trench gratings

Xiaoyi Liu<sup>1,2</sup>, Jinbo Gao<sup>1,2</sup>, Jinsong Gao<sup>1,2†</sup>, Haigui Yang<sup>1†</sup>, Xiaoyi Wang<sup>1</sup>, Tongtong Wang<sup>1</sup>, Zhenfeng Shen<sup>1</sup>, Zhen Liu<sup>1</sup>, Hai Liu<sup>1</sup>, Jian Zhang<sup>1</sup>, Zizheng Li<sup>1</sup>, Yanchao Wang<sup>1</sup> and Qiang Li<sup>1,2</sup>

In common plasmonic structures, absorption and radiation losses are often mutually restricted and can seriously influence the device performance. The current study presents a compound structure composed of multilayer grating stripes and multilayer shallow trenches. A small depth was adopted for the trench configuration to exclude the extra bend loss. These two sections supported Fabry-Perot resonance and cavity modes, respectively, with hybrid modes formed through intercoupling. In addition, the total loss for the entire framework was clearly reduced due to the introduction of the trench geometry, indicating that both absorption and radiation losses were successfully taken into consideration in the compound structure. Significantly, such a low loss realized by the hybridization of surface plasmon polariton modes has rarely been seen before. Moreover, the debatable relationship between the total and partial quality factors was described for the first time based on a hybrid mode analysis to establish a new approach to investigate the different resonance modes. In the detailed calculation process, the relative electric field intensity was first adopted to stipulate the effective areas for the various modes, which is more reasonable than using the common definition that is based on a unit structure. The multilayer trench grating exhibited a relatively low loss without weakening energy localization, which is significant in the design of plasmonic devices.

**Keywords:** surface plasmon polariton; multilayer trench grating; hybrid mode; quality factor

<sup>1</sup>Key Laboratory of Optical System Advanced Manufacturing Technology, Changchun Institute of Optics, Fine Mechanics and Physics, Chinese Academy of Sciences, Changchun 130033, China;

<sup>2</sup>University of the Chinese Academy of Sciences, Beijing 100039, China

†Correspondence: JS Gao, Email: gaojs@ciomp.ac.cn; HG Yang, Email: yanghg@ciomp.ac.cn

## INTRODUCTION

The utilization of surface plasmon polaritons (SPPs) to regulate the optical field and light-matter interaction on a sub-wavelength scale is a nanophotonics research hotspot<sup>1-5</sup>. As a special surface wave, SPPs can only propagate along the metal-insulator interface within a relatively thin range. In comparison, attenuation will simultaneously execute along the vertical direction. Accordingly, SPPs are capable of confining energy and enhancing local electromagnetic fields, which can lead to potential applications for surface-enhanced spectroscopy<sup>6,7</sup>, spacer<sup>8,9</sup>, solar cells<sup>10,11</sup>, hot carrier extraction technology<sup>12,13</sup>, metamaterials<sup>14,15</sup>, and high integration optical devices<sup>16,17</sup>, to name a few. To date, a variety of plasmonic microstructures have been extensively investigated, such as optical antennae<sup>18</sup>, grooves<sup>19</sup>, and one- or two-dimensional gratings<sup>20,21</sup>. The SPP penetration depth on the metal side is much smaller than that on the insulator side. As a result, a configuration based on an insulator layer sandwiched between two metal layers can be employed to further constrain light, thereby offering a wide range of applications for plasmonic waveguides or resonators<sup>22,23</sup>.

Although such a metal-insulator-metal (MIM) structure can show remarkable field localization, significant absorption loss is an inevitable problem due to the presence of the metal, which significantly influences surface wave propagation<sup>24</sup>. A relatively low absorption loss and long propagation distance can be obtained by weakening the metal's binding to the light, although this sacrifices certain characteristics of the MIM configuration<sup>25</sup>. In addition, the radiation loss for an open

architecture structure without a closed shell cannot be ignored<sup>24</sup>. The coupling and hybridization between different modes may suppress loss, which is usually observed in localized resonances supported by nano-disks or patches<sup>26-29</sup>. The coupling phenomenon can also be excited through propagating and non-propagating plasmonic modes supported by nano-rods, tubes or whispering gallery cavities<sup>30-33</sup>. However, research on low-loss structures based on hybrid SPP modes is rarely reported. Very recently, our previous work demonstrated an SPP mode hybridization phenomenon based on a multilayer trench grating geometry<sup>34</sup>, which led to the realization of a large absorption quality factor ( $Q$ ) in the trench configuration but lacked a quantitative analysis and verification of the entire loss inhibition. Furthermore, the microcavity electrodynamic processes in the hybrid SPP modes, specifically absorption, radiation, and connections between various losses, which are significant to the design of the plasmonic devices, all remain unclear.

In the present study, the Fabry-Perot (F-P) resonance modes and the cavity mode generated in the multilayer trench grating geometry are combined to form the hybrid modes under certain conditions. Compared with other mode-coupling approaches, the compound grating structure in this work is relatively low-cost and affords easy fabrication. Moreover, based on the nature of the F-P resonance, the hybrid-SPP modes always show multiple resonance orders, and all the resonant wavelengths depend linearly on the structure geometry, which offers a great design advantage for multi-band selection and regulation compared to other approaches and highlights potential to instigate plenty of applications. In the compound structure, a shallow trench was deliberately designed and fabricated to exclude interference originating from the bend loss. To

evaluate the total quality of the designed geometry, various microcavity electrodynamics aspects were investigated in detail for this compound structure, specifically the absorption and radiation processes, for which the results indicate a significant reduction in loss for the entire framework. Moreover, the total absorption  $Q$  was calculated according to the known absorption  $Q$  of the F-P mode and the cavity mode based on a calculation of their weighted averages, describing the undetermined relationship between the whole and part losses, which has not been previously reported in the literature. In the process of determining the weight coefficients, the relative electric field intensity was first adopted as the standard to stipulate the effective area of the various modes. The details of the research are presented below.

## METHODS

### Modeling and simulations

The compound structure was theoretically analyzed by the finite-difference time-domain method. In a series of simulations, the periodic condition was adopted as the boundary condition in both the X- and Y-directions. In addition, the perfectly matched layer condition was adopted in the Z-direction for the sake of extracting the reflectance spectra. The incident source is a linearly polarized plane wave, and the polarization direction is perpendicular to the gratings. The characteristic parameters for the Si material such as the permittivity and refractive index were obtained from the Palik database, and the Al parameters were obtained by CRC. Additionally, the calculations were repeatedly computed to guarantee accuracy for the simulations.

### Fabrication process

The designed multilayer trench grating was fabricated using the following process. Following surface oxidation layer chemical cleaning in hydrogen fluoride and acetone solutions, a 400-nm-thick photoresist was deposited onto a polished Si wafer by spin coating. The sample was then patterned by laser direct writing (LDW) lithography and subsequently developed in a NaOH solution for 35 s. The periodic trenches were then fabricated onto the sample by the reactive ion etching method in an SF<sub>6</sub> atmosphere. The etching process proceeded for 40 s to generate shallow trenches with a depth of approximately 450 nm. The sample was then soaked in an acetone solution to clear away residual photoresist; next, the film coating process was completed in a magnetron sputtering machine, which included deposition of five alternate Al and Si films. The Si layers had a thickness of 100 nm, and the Al layers had a thickness of 50 nm, which were optimized by the simulations. The grating constant for this structure was 2.5  $\mu\text{m}$ . The width ratio between the trench and grating was determined by the parameters of the LDW method. The present study generated four samples with different trench widths, specifically 1.1  $\mu\text{m}$ , 1.25  $\mu\text{m}$ , 1.4  $\mu\text{m}$  and 1.55  $\mu\text{m}$ , respectively. For the spectrum measurement, a spectrometer equipped with a 160-mm integrating sphere was used to measure the integrated reflectance ( $R$ ) of the fabricated samples between 500 nm and 2500 nm.

## RESULTS AND DISCUSSION

A diagram of the multilayer trench grating is shown in Fig. 1a. The compound structure is composed of two sections: a multilayer grating on the top and a multilayer trench at the bottom. Fig. 1b shows a photograph of the fabricated

sample. The top-view and cross-sectional scanning electron microscopy (SEM) images for the as-prepared microstructure are also shown. For convenience, the widths of the trench and grating stripe are set to  $W_1$  and  $W_2$ , respectively, as shown in Fig. 1c. Fig. 1d shows the local enlarged cross-sectional image of the sample and shows the grating and trench sections. However, the loss in this configuration is mainly derived from two aspects; specifically, the absorption and radiation, as shown in Fig. 1d. These properties cannot be assessed by the same method due to their different generative mechanisms. Moreover, the relationship between the losses for each individual structural part remains debatable and is carefully discussed in the following sections.

The five alternate Al and Si films formed two MIM waveguides in the multilayer grating stripe to sustain a gap plasmon mode with a relatively large propagation range<sup>24,30</sup>. Reflection was observed at the gap terminations due to the finite length of the waveguide, thereby resulting in the formation of an inner standing wave, which is a typical F-P resonance system with two distinct features, specifically, frequency sensitivity and multiple resonance orders<sup>34</sup>. The order of this F-P resonance mode is simply expressed as follows<sup>35,36</sup>:

$$m = \frac{W_2 \beta}{\pi} + \frac{\varphi_r}{2\pi} \quad (1)$$

where  $\varphi_r$  is the phase shift at the gap termination, which can be obtained by the linear fitting method; and  $\beta$  is the complex propagation constant, which can be calculated using dispersion equations derived from the symmetric waveguide theory with respect to the regular symmetric MIM waveguide, as carefully explained in our previous

work<sup>34</sup>. Apart from the calculation method, the resonance order  $m$  can also be directly obtained from the simulated electric field intensity distributions. Figs. 2a-d show the various electric field distributions for the multilayer grating stripe section in the XZ-plane with  $W_1=1.25 \mu\text{m}$ . According to the standing wave distribution characteristics, the resonance orders from the short wave to the long wave were directly and successively observed as  $m=11, 9, 7,$  and  $5$ . These four modes were labeled as  $F_4, F_3, F_2,$  and  $F_1$  and, respectively, correspond to Figs. 2a-d. The F-P modes were generated only at specific wavelengths and clearly showed frequency sensitivity for the F-P resonance. Furthermore, the resonance wavelengths were proportional to the waveguide length  $W_2$ , thereby indicating that an increase in  $W_1$  resulted in resonance peak blueshift phenomenon in the spectra. Fig. 2e shows the SEM images for the fabricated multilayer trench structures with  $W_1=1.1 \mu\text{m}, 1.25 \mu\text{m}, 1.4 \mu\text{m}$  and  $1.55 \mu\text{m}$ , respectively. To evaluate the various losses of the compound structure, the corresponding quality factors were calculated using appropriate approaches. First, the grating stripe absorption quality factor  $Q_{FP}^{abs}$  with negligible radiation is defined as<sup>24</sup>:

$$Q \cong \frac{\pi}{\lambda \text{Im}(\beta)} \quad (2)$$

where  $\lambda$  is the wavelength in free space; the propagation constant  $\beta$  can be solved by the dispersion equations. According to Eq. (2), both the simulated and experimental  $Q_{FP}^{abs}$  can be calculated even if they belong to different resonance orders or different waveguide lengths. Figs. 2f and 2g shows the results of the difference operation, which were calculated using the simulated and experimental data, respectively. The horizontal axis represents the resonance

modes from  $F_4$  to  $F_1$ , whereas the vertical axis represents the range of  $W_1$  from 1.1  $\mu\text{m}$  to 1.55  $\mu\text{m}$ . The color bar represents the value of  $Q_{FP}^{abs}$ . The series of simulations exhibited a  $W_1$  variation extent of 0.05  $\mu\text{m}$ . In other words, ten groups of simulated data were collected for the various  $W_1$  values. The  $Q_{FP}^{abs}$  values with relatively small  $W_1$  values or low resonance orders  $m$  were overall larger than the others, as observed in Fig. 2f. The result shown in Fig. 2g is in good agreement with the simulated result, though less experimental data were collected compared to the simulations. Generally, a negative correlation is observed between the quality factor and the loss. A maximum  $Q_{FP}^{abs}$  of only approximately 10 was observed, thereby implying that the absorption loss for the multilayer grating section was quite large and that the results were near the normal MIM configuration level<sup>24</sup>. The large absorption loss is inevitable due to the limitation of this configuration. However, with respect to the compound structure, more attention should be paid to loss evaluation for the entire framework, which can be regulated by the introduction of the trench section.

The absorption loss may be reduced by weakening the metal's binding to the light such as in an open half-space. The energy of the multilayer trench section was confined and weakened given that its core framework embodied an asymmetric insulator-metal-insulator (IMI) structure. Furthermore, this IMI configuration can be simplified to the interface between Al and air because the light hardly penetrated the first Al film. In addition, the energy was largely concentrated in the cavity of the trench, thereby resulting in the presence of the cavity resonance mode, which is another SPP mode with multiple resonance orders<sup>34</sup>. However, the present study only observed the first order in the concerned waveband. Compared with the

structures investigated in our previous work, the present study fabricated shallower trenches to avoid the interference originating from higher order cavity modes. More importantly, the shallow trench can eliminate the bend loss, which will be discussed later. The corresponding electric field distributions are presented in the next section, with a propagation constant  $\beta$  which is expressed as follows:

$$\beta = k_0 \sqrt{\frac{\epsilon_m \epsilon_{air}}{\epsilon_m + \epsilon_{air}}} \quad (3)$$

where  $\epsilon_m$  and  $\epsilon_{air}$  are the permittivities of Al and air, respectively, and  $k_0 = 2\pi/\lambda$  is the wave vector in free space. Consequently, the absorption quality factor  $Q_C^{abs}$  for the trench section can also be obtained by Eq. (2). For example, the simulated and experimental  $Q_C^{abs}$  with  $W_1 = 1.4 \mu\text{m}$  were approximately 1105.3 and 1728.5, respectively, and were generally two or three orders of magnitude higher than that of the F-P modes. The calculated results illustrate the ability of the trench section to increase the absorption quality factor  $Q_{tot}^{abs}$  for the entire framework. However, the detailed value remains unsolved. Additionally, the trench structure can generate additional radiation loss. As a result, it is unclear whether the total loss has increased or decreased. To solve these two problems, the total loss  $Q_{tot}$  for the entire structure must first be obtained.

Simply, the  $Q_{tot}$  can be extracted as  $Q = \lambda_r / \Delta\lambda$  by fitting the reflectance curve with a Lorentzian profile, where  $\lambda_r$  is the center wavelength of the resonance peak and  $\Delta\lambda$  is the full width at half-maximum (FWHM) of the resonance peak in the spectrum<sup>28,29,37,38</sup>. Fig. 3a shows the four cavity mode resonance peak spectra, which were

measured for the four fabricated samples with different  $W_l$  values, and successively treated by Lorentzian fitting, peak division and baseline calibration. The resonance wavelength of the cavity mode did not exhibit an obvious linear red- or blue- shift phenomenon following an increase in  $W_l$ . However, the cavity resonance mode successively coupled with the F-P modes due to the presence of regular F-P mode blueshifts, thereby resulting in the generation of hybrid modes. Fig. 3b shows the variation trend for the total quality factor  $Q_{tot}$ , which included all the F-P modes and the cavity mode. Similar to Figs. 2f and 2g, 10 groups of simulated data (solid line) and 4 groups of experimental data (dash line) with various  $W_l$  are given in Fig. 3b. In addition, the F-P modes from  $F_4$  to  $F_1$  were fixed as the horizontal axis. The vertical axis represents the value of  $Q_{tot}$ , and each subgraph ranged from 0 to 80. An increase in the trench width  $W_l$  successively merges the cavity mode  $C$  with the F-P modes. More concretely, when  $W_l=1.1 \mu\text{m}$ , mode  $C$  was independent from the F-P modes; when  $W_l=1.15 \mu\text{m}$ , mode  $C$  merged with mode  $F_4$ , thereby generating hybrid mode  $C+F_4$ . Similarly, at  $W_l=1.2 \mu\text{m}$ , a hybrid mode  $C+F_3$  was generated. In addition, mode  $C$  was observed between  $F_3$  and  $F_2$  following an increase in  $W_l$  to  $W_l=1.25 \mu\text{m}$ ,  $1.3 \mu\text{m}$ , or  $1.35 \mu\text{m}$ . The formation of a hybrid mode  $C+F_2$  was observed when  $W_l=1.4 \mu\text{m}$ . Mode  $C$  was observed between  $F_2$  and  $F_1$  as  $W_l$  to  $W_l=1.45 \mu\text{m}$ ,  $1.5 \mu\text{m}$ , or  $1.55 \mu\text{m}$ . These mode coupling trends were also observed in the electric field intensity distributions. Figs. 3c-1 show the electric field distributions for the cavity mode  $C$  in the XZ-plane with various  $W_l$  values, which correspond to the ten subgraphs in Fig. 3b. The relative positions between the different modes are largely represented by the resonance order  $m$  of the F-P modes. For instance, in Fig. 3c, the resonance order  $m$  is larger

than 11, indicating that the cavity mode is beyond the F-P modes. Similarly, in Fig. 3d,  $m=11$ , which represents the hybrid mode of  $C+F_4$ , and so on. Therefore, the reflectance spectrum for  $W_l=1.4 \mu\text{m}$  in Fig. 3a represents the peak for the hybrid mode  $C+F_2$ . In addition to the trends for the modes coupling, more importantly, the cavity mode also has a relatively large  $Q_{tot}$ , as well as the hybrid modes, especially in the relatively long wave range. Even compared with completely optimized Ag-GaAs-Ag structures<sup>39</sup>, the values of  $Q_{tot}$  in the present study were at least twice as large as their results under an identical thickness of the insulator layer. This is the most important conclusion with respect to the compound trench grating structure, offering a great significance for the design of hybrid-plasmonic devices. The experimental results accorded well with the calculated results, though some numerical differences were observed due to deviations in the simulations and the fabrication process. These significant results illustrate the inhibitive effect on the total loss due to the introduction of the trench structure. Additionally, the concentration of energy in the cavity validated the reliability of the simplified analysis for calculation of the propagation constant  $\beta$ .

It is remarkable that all the  $Q_{FP}^{abs}$ ,  $Q_C^{abs}$  and  $Q_{tot}$  values for several hybrid modes were obtained, thereby providing a possibility for further investigation. Here, the hybrid mode  $C+F_4$  with  $W_l=1.15 \mu\text{m}$  was renamed as  $H_3$ , and the hybrid mode  $C+F_3$  with  $W_l=1.2 \mu\text{m}$  was renamed as  $H_2$ . The simulated and experimental hybrid modes  $C+F_2$  with  $W_l=1.4 \mu\text{m}$  were renamed as  $H_1$  and  $H_1^{exp}$ , respectively. Before discussing the microcavity electrodynamic characteristics for the compound structure, all the interference and losses must be excluded except the absorption and radiation processes. As mentioned before,

the shallow trench was deliberately designed and fabricated to avoid bend loss. According to the research reported by Vlasov et al., there is a negative exponential functional relationship between bending radius and bend loss<sup>40</sup>. In the present study, the large radius represents a shallow trench. Accordingly, a series of simulations were carried out to verify whether the trench is shallow enough to safely neglect the bend loss. As shown in Fig. 4, the simulations focused on the hybrid modes  $H_3$ ,  $H_2$ , and  $H_1$ , and kept all the corresponding structure parameters the same except the trench depth. For example, Figs. 4a and 4d show the electric field intensity distributions for  $H_3$  with deep and ultra-shallow trenches, respectively. The different trench shapes imply that compared with the normal shallow trench, the deep trench has an obviously smaller radius, while the ultra-shallow trench shows the opposite behavior. Fig. 4g shows the reflectance spectra for  $H_3$  in the case of deep and ultra-shallow trenches, with the corresponding FWHM also given. Clearly, the latter structure shows a narrower spectrum peak compared to the former. According to the equation  $Q = \lambda_r / \Delta\lambda$ , the ultra-shallow trench structure also has a larger total  $Q$  factor, as shown in Fig. 4j. The pink dashed line represents the corresponding  $Q$  value belonging to the normal shallow trench structure, which is very close to the value obtained for the ultra-shallow structure. Since all the structure parameters are unchanged except the trench depths, the differences in the  $Q$  values can be completely attributed to the bend loss. The results illustrate that with increasing radius, the bend loss clearly decreases; however, if the radius is large enough, the bend loss will become very small and tend to be stable. Similarly, the hybrid modes  $H_2$  (shown in Fig. 4, second column) and  $H_1$  (shown in Fig. 4, third column) show the same conclusions. This variation trend accords

well with the conclusions of Vlasov et al., signifying that the bend loss can be safely neglected for the normal shallow trench in the present study. Based upon this condition, the absorption and radiation characteristics in the compound structure can be further discussed.

First, the total radiation quality factor  $Q_{tot}^{rad}$  for the entire structure was calculated based on the value of  $Q_{tot}$  and the reflectance spectrum. According to the coupled mode theory, the reflectance is expressed as follows<sup>29,41</sup>:

$$R(\omega) = 1 - \frac{A_c}{A_i} + \frac{A_c}{A_i} \left| \frac{\frac{\omega}{Q_{tot}^{rad}}}{i(\omega - \omega_r) + \frac{\omega}{2Q_{tot}}} - 1 \right|^2 \quad (4)$$

where  $\omega$  is the incident frequency;  $\omega_r$  is the resonance frequency; and  $A_c/A_i$  is the ratio between the effective aperture of the microstructure and the spot size of the incidence beam, which represents the light coupling efficiency<sup>29</sup>. The simulations followed an  $A_c/A_i$  of 1. In practical measurements, the integrated reflectance is obtained by the integrating sphere to minimize energy collection waste. However, unpolarized light was used to measure the fabricated grating-shaped microstructure in the spectrometer. Consequently, half of the light was not considered in the coupling process, thereby altering the  $A_c/A_i$  to 0.5 in the experiments. Subsequently, when  $\omega = \omega_r$ , the value of  $Q_{tot}^{rad}$  is expressed as follows:

$$Q_{tot}^{rad} = \frac{2Q_{tot}}{1 + \sqrt{1 + \frac{A_i}{A_c} [R(\omega_r) - 1]}} \quad (5)$$



where  $Q_{tot}^{rad}$  is calculated by substituting the value of  $Q_{tot}$ ,  $R(\omega_r)$ , and  $A_i/A_c$  into the above equation. As mentioned above, it is still unclear whether quality factor calculations can proceed using the quality factors of individual sections for the entire framework. It is hard to treat the various types of  $Q$  factors by a unified approach, which is a fundamental difficulty. In terms of absorption, the compound structure in the final analysis supported two modes with different propagation constants  $\beta$ , which challenged the establishment of connections between  $Q_{FP}^{abs}$  and  $Q_C^{abs}$ . Clearly, the reference value for the total absorption quality factor  $Q_{tot}^{abs}$  can first be obtained based on the following relationship<sup>29</sup>:

$$\frac{1}{Q_{tot}} = \frac{1}{Q_{tot}^{abs}} + \frac{1}{Q_{tot}^{rad}} \quad (6)$$

Notably, the values of  $Q_{tot}^{abs}$  were two orders of magnitude higher than the values of  $Q_{FP}^{abs}$ , which verified that the SPP-mode hybridization can effectively reduce the loss, whatever the total or the absorption one. Subsequently, the total absorption quality factor can also be obtained using a reasonable fitting method with the known values for  $Q_{FP}^{abs}$  and  $Q_C^{abs}$ . The precision of the fitting method can be evaluated based on a comparison of these two results. Therefore, the core of the problem lies in the determination of a reasonable fitting approach. For example, the total quality factor of two identical structures must be equal to the value of each independent structure, which challenges the use of the reciprocal operation such as that used in Eq. (6). As a result, the present study used the calculated weighted average as the fitting method, and the weight coefficients were determined by the energies of the two modes, which cannot be measured directly. The energy

ratio between the two polarization states for the paired nano-disk structures was obtained by rotating the polarizer<sup>28</sup>. However, this was not applicable to our case. Accordingly, a new approach must be proposed, which must be able to avoid the difficulties of distinguishing two modes on a subwavelength scale, and precisely reflect the energy weights of the two modes in the coupling process. Due to the one-dimensional grating-shaped framework, the effective mode area  $\sigma_{eff}$  was defined in the XZ-plane without considering the energy distribution along the Y-axis. Specifically, the use of  $\sigma_{eff}$  indicates that the relative electric field intensity  $E$  in the area, which was standardized by the incident electric field intensity, satisfies the relationship:  $E > E_{max}/e$ , where  $E_{max}$  is the maximum electric field intensity in the mode area. This method precisely quantifies the major energy distribution area in all modes and is considered to be more reasonable than a definition based on the structure of the periodic unit cells<sup>28</sup>. The fitted value  $\bar{Q}_{tot}^{abs}$  is defined as  $\bar{Q}_{tot}^{abs} = p Q_{FP}^{abs} + q Q_C^{abs}$ , such that the weight coefficients determined by the energies can be expressed as:

$$p = \frac{\int_{\sigma_{eff}^{FP}} \epsilon_d |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r}}{\int_{\sigma_{eff}^{FP}} \epsilon_d |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r} + \int_{\sigma_{eff}^C} \epsilon_{air} |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r}} \quad (7)$$

$$q = \frac{\int_{\sigma_{eff}^C} \epsilon_{air} |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r}}{\int_{\sigma_{eff}^{FP}} \epsilon_d |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r} + \int_{\sigma_{eff}^C} \epsilon_{air} |\mathbf{E}(\mathbf{r})|^2 d\mathbf{r}} \quad (8)$$

where  $\sigma_{eff}^{FP}$  and  $\sigma_{eff}^C$  are the effective mode areas for the F-P mode and the cavity mode, respectively; and  $\epsilon_d$  is the complex permittivity of Si. Fig. 5a shows the values of  $\sigma_{eff}^{FP}$

and  $\sigma_{eff}^C$  for the three hybrid modes, specifically  $H_3$ ,  $H_2$  and  $H_1$  (left axis), and the energy ratio  $p_1/q_1$  of the hybrid modes (right axis). Mode  $H_1^{exp}$  can invoke the coefficients of mode  $H_1$  in the fitting process. Accordingly, the value of  $\bar{Q}_{tot}^{abs}$  can be fitted by calculating the weighted average using the above coefficients. Fig. 5b shows the values of  $Q_{tot}^{rad}$ ,  $Q_{tot}^{abs}$ , and  $\bar{Q}_{tot}^{abs}$  for several hybrid modes. Considering the latter two are one order of magnitude higher than the other quality factors and their deviations easily increase, the results for the fitted  $\bar{Q}_{tot}^{abs}$  are in very good accordance with the values for  $Q_{tot}^{abs}$ . Subsequently, the fitted  $\bar{Q}_{tot}^{abs}$  was adopted to solve the total quality factor using Eq. (6), which is represented as  $\bar{Q}_{tot}$ . Fig. 5c shows comparisons between the values of  $\bar{Q}_{tot}$  obtained by the fitting method and the results directly extracted from  $Q_{tot}=\lambda_r/\Delta\lambda$ . In general, the results for  $\bar{Q}_{tot}$  were close to the values for  $Q_{tot}$ , which indicates the reliability of the presented approach to calculate the weighted average and the accuracy of the weight coefficients in the fitting process. By virtue of such a pure mathematical method, that one can estimate for the first time the quality factor for the entire framework from the known quality factors for the individual sections, which offers a new insight for investigating various kinds of plasmonic modes, even with different propagation constants.

Additionally, the trade-off between loss and energy confinement is one of the most important principles and considerations when designing a high-performance plasmonic device<sup>30</sup>. Referring to the concept of the Purcell factor<sup>42,43</sup>, the values of  $Q_{tot}/\sigma_{eff}^{tot}$  ( $\sigma_{eff}^{tot}=\sigma_{eff}^{FP}+\sigma_{eff}^C$ ) were characterized to evaluate the relationship between energy

localization and loss for the entire framework, as shown in Fig. 5d. Similar to previous calculations, the  $H_1^{exp}$  mode invokes the relevant parameters of the  $H_1$  mode to obtain the ratio. Moreover, the values for  $Q_{FP}^{abs}/\sigma_{eff}^{FP}$  were also characterized for reference. As known, the MIM has a great ability to confine light, thereby generating a relatively small  $\sigma_{eff}^{FP}$ . In Fig. 5d, the two groups of data showed the same order of magnitude, which illustrates the strong energy confinement and relatively low loss in the compound multilayer trench grating structure.

## CONCLUSIONS

In summary, a MIM configuration strongly confines light into a relatively small space despite the generation of a relatively large absorption loss. In contrast, a semi-open asymmetric IMI configuration generally exhibits serious radiation loss instead of absorption. In this work, a compound multilayer trench grating structure was demonstrated, which includes grating stripes and shallow trench sections. The former geometry formed F-P resonance modes in the MIM waveguides with frequency sensitivity and multiple resonance orders. Serious absorption loss was evaluated by calculating the relevant quality factor. However, based on the cavity mode generated in the trenches, the latter geometry showed a relatively low absorption loss. The shallow trench in the present study was deliberately designed and fabricated to avoid bend loss. In addition, the total loss for the entire structure decreased following the introduction of the trench configuration, thereby illustrating the ability of the compound framework to simultaneously consider absorption and radiation loss. Furthermore, according to investigations of the hybrid modes, which were formed by the F-P and cavity modes, the total quality factor was fitted

by calculating the weighted average of the partial values of the individual sections, which described their previously undetermined relationship. In this process, the effective area of the different modes was stipulated by the relative electric field intensity, which was more reasonable than the common definition based on a unit structure. Finally, the ratio between the quality factor and the effective mode area for the compound framework was characterized. The results indicate the ability of the multilayer trench grating to reduce loss without weakening energy confinement, which can fill a gap in the field of hybrid-SPP-based high-quality plasmonic structures.

#### ACKNOWLEDGMENTS

Project supported by the National Natural Science Foundation of China (Nos. 61675199, U1435210, 61705226, 61705224, and 11604329).

#### REFERENCES

- Sandtke M, Kuipers L. Slow guided surface plasmons at telecom frequencies. *Nat Photonics* 2007; **1**: 573-576.
- Berini P, De Leon I. Surface plasmon-polariton amplifiers and lasers. *Nat Photonics* 2012; **6**: 16-24.
- Zhang JJ, Liao Z, Luo Y, Shen XP, Maier SA *et al*. Spoof plasmon hybridization. *Laser Photonics Rev* 2017; **11**: 1600191.
- Zhu Y, Hu XY, Yang H, Gong QH. On-chip plasmon-induced transparency based on plasmonic coupled nanocavities. *Sci Rep* 2014; **4**: 3752.
- Pan BC, Zhang HC, Cui TJ. Multilayer transmissions of spoof surface Plasmon polaritons for multifunctional applications. *Adv Mater Technol* 2017; **2**: 1600159.
- Camden JP, Dieringer JA, Zhao J, Van Duyne RP. Controlled plasmonic nanostructures for surface-enhanced spectroscopy and sensing. *Acc Chem Res* 2008; **41**: 1653-1661.
- Vesseur EJR, de Waele R, Kuttge M, Polman A. Direct observation of plasmonic modes in au nanowires using high-resolution cathodoluminescence spectroscopy. *Nano Lett* 2007; **7**: 2843-2846.
- Li DB, Stockman MI. Electric spaser in the extreme quantum limit. *Phys Rev Lett* 2013; **110**: 106803.
- Oulton RF, Sorger VJ, Zentgraf T, Ma RM, Gladden C *et al*. Plasmon lasers at deep subwavelength scale. *Nature* 2009; **461**: 629-632.
- Pala RA, White J, Barnard E, Liu J, Brongersma ML. Design of plasmonic thin-film solar cells with broadband absorption enhancements. *Adv Mater* 2009; **21**: 3504-3509.
- Su YH, Ke YF, Cai SL, Yao QY. Surface plasmon resonance of layer-by-layer gold nanoparticles induced photoelectric current in environmentally-friendly plasmon-sensitized solar cell. *Light Sci Appl* 2012; **1**: e14.
- Brongersma ML, Halas NJ, Nordlander P. Plasmon-induced hot carrier science and technology. *Nat Nanotechnol* 2015; **10**: 25-34.
- Knight MW, Wang YM, Urban AS, Sobhani A, Zheng BY *et al*. Embedding plasmonic nanostructure diodes enhances hot electron emission. *Nano Lett* 2013; **13**: 1687-1692.
- Kabashin AV, Evans P, Pastkovsky S, Hendren W, Wurtz GA *et al*. Plasmonic nanorod metamaterials for biosensing. *Nat Mater* 2009; **8**: 867-871.
- Henzie J, Lee MH, Odom TW. Multiscale patterning of plasmonic metamaterials. *Nat Nanotechnol* 2007; **2**: 549-554.
- Zhang WH, Ding F, Li WD, Wang YX, Hu J *et al*. Giant and uniform fluorescence enhancement over large areas using plasmonic nanodots in 3D resonant cavity nanoantenna by nanoimprinting. *Nanotechnology* 2012; **23**: 225301.
- Ding K, Ning CZ. Metallic subwavelength-cavity semiconductor nanolasers. *Light Sci Appl* 2012; **1**: e20.
- Lin KT, Chen HL, Lai YS, Yu CC. Silicon-based broadband antenna for high responsivity and polarization-insensitive photodetection at telecommunication wavelengths. *Nat Commun* 2014;

- 5: 3288.
- 19 Li XE, Jiang T, Shen LF, Deng XH. Subwavelength guiding of channel plasmon polaritons by textured metallic grooves at telecom wavelengths. *Appl Phys Lett* 2013; **102**: 031606.
  - 20 Sobhani A, Knight MW, Wang YM, Zheng B, King NS *et al.* Narrowband photodetection in the near-infrared with a plasmon-induced hot electron device. *Nat Commun* 2013; **4**: 1643.
  - 21 Li W, Valentine J. Metamaterial perfect absorber based hot electron photodetection. *Nano Lett* 2014; **14**: 3510-3514.
  - 22 Ji DX, Song HM, Zeng X, Hu HF, Liu K *et al.* Broadband absorption engineering of hyperbolic metafilm patterns. *Sci Rep* 2014; **4**: 4498.
  - 23 Lee KT, Seo SY, Guo LJ. High-color-purity subtractive color filters with a wide viewing angle based on plasmonic perfect absorbers. *Adv Opt Mater* 2015; **3**: 347-352.
  - 24 Bozhevolnyi SI, Søndergaard T. General properties of slow-plasmon resonant nanostructures: nano-antennas and resonators. *Opt Express* 2007; **15**: 10869-10877.
  - 25 Oulton RF, Sorger VJ, Genov DA, Pile DFP, Zhang X. A hybrid plasmonic waveguide for subwavelength confinement and long-range propagation. *Nat Photonics* 2008; **2**: 496-500.
  - 26 Vecchi G, Giannini V, Rivas JG. Shaping the fluorescent emission by lattice resonances in plasmonic crystals of nanoantennas. *Phys Rev Lett* 2009; **102**: 146807.
  - 27 Rodriguez SRK, Abass A, Maes B, Janssen OTA, Vecchi G *et al.* Coupling bright and dark plasmonic lattice resonances. *Phys Rev X* 2011; **1**: 021019.
  - 28 Todisco F, Esposito M, Panaro S, De Giorgi M, Dominici L *et al.* Toward cavity quantum electrodynamics with hybrid photon gap-Plasmon states. *ACS Nano* 2016; **10**: 11360-11368.
  - 29 Seok TJ, Jamshidi A, Kim M, Dhuey S, Lakhani A *et al.* Radiation engineering of optical antennas for maximum field enhancement. *Nano Lett* 2011; **11**: 2606-2610.
  - 30 Wang JF, Zhang C, Zhang JX, Song HJ, Wang P *et al.* Hybrid plasmonic cavity modes in arrays of gold nanotubes. *Adv Opt Mater* 2017; **5**: 1600731.
  - 31 Lyvers DP, Moon JM, Kildishev AV, Shalaev VM, Wei A. Gold nanorod arrays as plasmonic cavity resonators. *ACS Nano* 2008; **2**: 2569-2576.
  - 32 Song HJ, Zhang JX, Fei GT, Wang JF, Jiang K *et al.* Near-field coupling and resonant cavity modes in plasmonic nanorod metamaterials. *Nanotechnology* 2016; **27**: 415708.
  - 33 Wang P, Wang YP, Yang ZY, Guo X, Lin X *et al.* Single-band 200-nm-line-width plasmon resonance in a strongly coupled Au nanorod. *Nano Lett* 2015; **15**: 7581-7586.
  - 34 Liu XY, Gao JS, Yang HG, Wang XY, Tian SC *et al.* Hybrid plasmonic modes in multilayer trench grating structures. *Adv Opt Mater* 2017; **5**: 1700496.
  - 35 Hu FF, Yi HX, Zhou ZP. Band-pass plasmonic slot filter with band selection and spectrally splitting capabilities. *Opt Express* 2011; **19**: 4848-4855.
  - 36 Bora M, Behymer EM, Dehlinger DA, Britten JA, Larson CC *et al.* Plasmonic black metals in resonant nanocavities. *Appl Phys Lett* 2013; **102**: 251105.
  - 37 Li ZY, Butun S, Aydin K. Ultranarrow band absorbers based on surface lattice resonances in nanostructured metal surfaces. *ACS Nano* 2014; **8**: 8242-8248.
  - 38 Campione S, Liu S, Basilio LI, Warne LK, Langston WL *et al.* Broken symmetry dielectric resonators for high quality factor fano metasurfaces. *ACS Photonics* 2016; **3**: 2362-2367.
  - 39 Yang J, Sauvan C, Jouanin A, Collin S, Pelouard JL *et al.* Ultrasmall metal-insulator-metal nanoresonators: impact of slow-wave effects on the quality factor. *Opt Express* 2012; **20**: 16880-16891.
  - 40 Vlasov YA, McNab SJ. Losses in single-mode silicon-on-insulator strip waveguides and bends. *Opt Express* 2004; **12**: 1622-1631.
  - 41 Hamam RE, Karalis A, Joannopoulos JD, Soljačić M. Coupled-mode theory for general free-space resonant scattering of waves. *Phys Rev A* 2007; **75**: 053801.
  - 42 Kristensen PT, Van Vlack C, Hughes S. Generalized effective mode volume for leaky optical cavities. *Opt Lett* 2012; **37**: 1649-1651.
  - 43 Sauvan C, Hugonin JP, Maksymov IS, Lalanne P. Theory of the spontaneous optical emission of

nanosize photonic and Plasmon resonators. *Phys Rev*

*Lett* 2013; **110**: 237401.

Accepted Manuscript

## List of Figure Captions

**Figure 1.** (a) Diagram of the designed multilayer trench grating microstructure. (b) A photograph of the fabricated sample. (c) Top-view SEM image of the fabricated multilayer trench gratings, with a scale bar of 2  $\mu\text{m}$ . (d) Cross-sectional SEM image of the fabricated multilayer trench gratings, with a scale bar of 0.5  $\mu\text{m}$ . The major Microcavity electrodynamic processes in this compound structure are shown.

**Figure 2.** (a-d) Electric field distributions for the multilayer grating stripe section in the XZ-plane with F-P resonance order  $m=11, 9, 7,$  and  $5,$  respectively. The trench width  $W_I$  is 1.25  $\mu\text{m}$ . The color bar denotes the relative electric field intensity with a range from 0 to 2.5. (e) Cross-sectional SEM images of the fabricated multilayer trench gratings with  $W_I=1.1 \mu\text{m}, 1.25 \mu\text{m}, 1.4 \mu\text{m},$  and  $1.55 \mu\text{m},$  respectively. (f-g) Simulated and experimental  $Q_{FP}^{abs}$  for the multilayer grating stripe section. The F-P modes from  $F_4$  to  $F_1$  are fixed as the horizontal axis, while the vertical axis represents the different  $W_I,$  corresponding to Fig. 2e. The color bar denotes the values of  $Q_{FP}^{abs}$  with a range from 1.64 to 10.

**Figure 3.** (a) Measured reflectance spectra for the cavity mode with  $W_I=1.1 \mu\text{m}, 1.25 \mu\text{m}, 1.4 \mu\text{m},$  and  $1.55 \mu\text{m},$  respectively. The spectra are successively treated by Lorentzian fitting, peak division and baseline calibration. (b) 10 groups of simulated  $Q_{tot}$  (solid line) and 4 groups of experimental  $Q_{tot}$  (dash line) with different  $W_I.$  The F-P modes from  $F_4$  to  $F_1$  are fixed as the horizontal axis. The vertical axis represents the value of  $Q_{tot};$  the range for each subgraph is from 0 to 80. (c-l) Electric field distributions for the cavity mode in the XZ-plane with different  $W_I,$  corresponding to Fig. 3b. The color bars denote the relative electric field intensity ranging from 0 to 4.

**Figure 4.** (a-c) Electric field intensity distributions for  $H_3, H_2,$  and  $H_1$  with the deep trenches in the XZ-plane, respectively. The color bar ranges from 0 to 4. (d-f) Electric field intensity distributions for  $H_3, H_2,$  and  $H_1$  with the ultra-shallow trenches in the XZ-plane, respectively. The color bar ranges from 0 to 4. (g-i) Comparisons between the reflectance spectra with deep and ultra-shallow trenches in  $H_3, H_2,$  and  $H_1,$  respectively. (j-l) Comparisons between the  $Q$  factors with deep and ultra-shallow trenches in  $H_3, H_2,$  and  $H_1,$  respectively. The pink dashed lines are the corresponding  $Q$  values for the normal shallow trench structure.

**Figure 5.** (a) Effective mode area  $\sigma_{eff}^{FP}, \sigma_{eff}^C$  (left axis) and the energy ratio  $p/q$  (right axis) in hybrid modes  $H_3, H_2,$  and  $H_1,$  respectively. (b) Values for  $\bar{Q}_{tot}^{abs}, Q_{tot}^{abs}$  and  $Q_{tot}^{rad}$  in hybrid modes  $H_3, H_2, H_1,$  and  $H_1^{exp}$  respectively. (c) Values for  $\bar{Q}_{tot}$  and  $Q_{tot}$  in hybrid modes  $H_3, H_2, H_1,$  and  $H_1^{exp}$  respectively. (d) Comparison between  $Q_{tot}/\sigma_{eff}^{tot}$  and  $Q_{FP}^{abs}/\sigma_{eff}^{FP}$  in hybrid modes  $H_3, H_2, H_1,$  and  $H_1^{exp},$  respectively.











